
Drill Core Samples Received
ore
Samples Dried, Composite and Split
crush and milling
Head Assay Analysis
- Au Analysis
- Au Screen Fire Assay
- Total Carbon
- Total Organic Carbon
- Total Sulfur
Grind Establishment time & Au by Size Distribution Gold
Gravity Gold (Knelson Concentrator)
gravity concentrated 20-21%
Knelson Tail undergo CIL
Knelson Concentrate Undergo Intensive Leach
CIL, the recovery is >70%
Intensive leach >90%